

## Simprex<sup>®</sup> M745-200

*203-284°F (95-140°C) Curing Vinyl Ester Prepreg*

### Description

---

Simprex<sup>®</sup> M745-200 is an advanced vinyl ester prepreg with low styrene emission designed to provide a high performance-to-cost ratio. It has a medium to high tack and provides good adhesion to core materials such as Nomex<sup>®</sup> honeycomb, balsa and foams. Simprex<sup>®</sup> M745-200 can be cured at a lower temperature (203°F), than standard Prepregs, within **8 hours**. Simprex<sup>®</sup> M745-200 is a great choice for many low service temperature applications.

### Features

---

#### • Prepreg

- ❖ Fast curing cycle: 15-20 min @ 250-257°F.
- ❖ Suitable for low pressure: 1-3 bar.
- ❖ Excellent flexibility and handling.
- ❖ Environmentally friendly and retains its tack for many days.
- ❖ Controlled flow for ease processing (autoclave, press-mold & vacuum bagging).
- ❖ Weight loss < 1%, as determined in a vacuum curing process.

#### • Laminate

- ❖ Superior toughness and excellent fatigue resistance.
- ❖ Good resistance to a broad range of organic and inorganic acids, alkalis, oxidizing chemical and salt solutions, commonly up to 203°F (95°C).

### Physical Properties on 7781 E-Glass Fabric

---

- Standard weight: 0.092 lbs/sq. ft. (484 g/m<sup>2</sup>).
- Standard resin content: 38% by weight.
- Standard tack: good tack on both sides.
- Cured ply thickness: 0.010" (0.254 mm).

### Typical Applications

---

- FRP parts for chemical resistance purposes.
- General-purpose composites.
- High performance sporting goods.
- Racing vehicles.

### Shelf Life

---


- 6 months @ 68°F (20°C)

## Curing Conditions

As illustrated in the following Figure, the curing temperature should increase from 95°C till 125°C, over a storing period of 6 months @ 20°C.

Normal curing cycle is **15-20 min @ 250-257°F (121-125°C), under 1-3 bars pressure**. In press-mold, pressure should increase gradually to reach its maximum within 60-90 sec. In some applications, a **post-cure @ 284-293°F (140-145°C)**, is required for optimum performance.

- It must be understood that the curing time starts only after the prepreg temperature achieves the recommended temperature. This involves a dwell time which depends on the heating rate.



## Laminate Properties

✓ Glass Transition Temperature (DSC): 120-125°C

Mechanical Properties	ASTM	E-Glass 7781 ■	E-Glass 7781 * <sup>♣</sup>	Carbon 12K Stitched UD – (T700.) * <sup>♣</sup>
<b>Flexural</b> Strength, MPa Modulus, GPa	D-790	550-600 22-24	TBD TBD	1300-1440 109-110
<b>Tensile</b> Strength, MPa Modulus, GPa	D-3039	TBD TBD	TBD TBD	TBD TBD
<b>Compression</b> Strength, MPa Modulus, GPa	D-695	TBD TBD	TBD TBD	TBD TBD
<b>Inter-laminar Shear</b> Strength, MPa	D-2344	48-52	TBD	75-84

■ Laminate cured in press @ 121°C / 20 min / 3 bars, and then post-cured @ 140°C / 20 min.

♣ Laminate cured under vacuum @ 121°C / 20 min, and then post-cured @ 140°C / 20 min.

## Storage and Handling

---

All Simprex® preregs are wrapped in a shrink film immediately after impregnation and then packed into a barrier film.

Simprex® preregs should be stored in their original packaging barrier film, or an equivalent film, and maintained airtightness, at 68°F (20°C) and dry place.

If the prepreg roll has to be maintained out of its packaging barrier film, for few hours during lamination and processing time, it should be wrapped up again in a shrink film. This will protect the prepreg and extend its out of the bag life time.

The small prepreg pieces that were cut from the roll in order to be laminated should be handled and protected properly. The release film must not be removed from the prepreg piece only when ready to be placed and laminated in the mold. The top release film must not be removed only when the following prepreg layer is ready to be placed. Such lamination care will ensure minimum styrene emission and working area highly environmentally friendly. The prepreg tack time out of the barrier packaging bag will be for several days, depending on the previous handling and protective caring.

## Safety Precautions

---

Usual precautions should be observed. The prepreg contains mainly uncured synthetic resins. The operator has to use appropriate mask – respirator and work in a clean, dry (R.H. = 50% or less), and ventilated area. The use of clean disposable inert gloves provides protection for the operator and avoids contamination of material and components.

## Important Notice

---

The data reported in this sheet are based on representative samples. Since the method and circumstances of handling and processing are keys to the material performance, Gulf Composite Materials L.L.C., does not guaranty these data. Users should make their own assessment of the suitability of any product for the performance required.